



DUPONT™ PYRALUX® LG FLEXIBLE COMPOSITES

IMPREGNATED GLASS FABRIC

DESCRIPTION

Pyralex® LG impregnated glass fabric composites combine the features of a proprietary B-staged modified acrylic adhesive with the stability and mechanical toughness of woven glass fabric. These composites are primarily used in heat sink bonding applications that require additional resistance to distortion in handling.

SPECIFICATIONS

- Impregnated glass fabric composites
- Certified to IPC-4203/17

Typical physical and electrical properties along with applicable test methods are shown in **Table 2**.

CONSTRUCTION

Standard Pyralux® LG products are listed in Table 1. Impregnated glass fabric composites are available in two pressed thicknesses and two resin content levels.

PACKAGING

Pyralex® LG impregnated glass fabric composites are supplied on 18 in (457 mm) or 36 in (914 mm) wide rolls. The minimum roll length is 300 ft (9.1 m). Other sizes are available by special order. All packaging materials are 100% recyclable.

PROCESSING

Laminating conditions for Pyralux® flexible composites are typically in the following ranges:

Part Temperature: 182–199°C (360–390°F)

Pressure: 14–28 kg/cm² (200–400 psi)

Time: 1–2 hours, at temperature

Hard press pad systems are recommended. If soldered plated-through holes are present, it may be necessary to use laminating temperatures at the low end of the range and pressures reduced to 6–9 kg/cm² (90–130 psi). However, when laminating below 177°C (350°F) extended time beyond

90 minutes may be required to achieve a complete cure level for high bond strengths, good chemical resistance and good solder resistance. Pyralux® impregnated glass fabric composites will not flow appreciably during lamination. If adhesive encapsulation of circuits is needed, a sheet of adhesive from the Pyralux® product line can be included in the lay-up.

STORAGE CONDITIONS AND SHELF LIFE

Pyralex® flexible composites are warranted for one year when stored in the original packaging at temperatures of 4–29°C (40–85°F) and below 70% relative humidity. The products do not require refrigeration and should not be frozen. The material should be kept clean and well protected from physical damage.

SAFE HANDLING

Pyralex® impregnated glass fabric composites contain a B-staged adhesive. Since B-staged adhesive contains trace quantities (parts per million) of unreacted monomers, operators should take care to minimize contact. Although DuPont is not aware of anyone developing contact dermatitis when using Pyralux®, some individuals may be more sensitive than others.

Anyone handling Pyralux® should wash their hands with soap before eating, smoking or using restroom facilities. Gloves and finger pads should be changed daily. Wash protective clothing frequently.

The uncured monomers in the adhesive may impart a mild odor when the protective Mylar® polyester film is removed in lay-up, or when the composite is laminated. Air sampling tests indicate no cause for concern. However, it is recommended that lay-up and lamination areas be well-ventilated, preferably with a fresh air make-up supply.

Pyralex® flexible laminates do not contain polybrominated biphenyls (PBBs) or polybrominated biphenyl oxides (PBBOs).



DUPONT™ PYRALUX® LG FLEXIBLE COMPOSITES

Table 1. Impregnated Glass Fabric Product Codes

Product Code	Resin Content Percent	Pressed Thickness	
		mils/ply	(mm/ply)
LG 1000	65 ± 10	5 ± 10%	(127 ± 10%)
LG 1062	TBD	2 ± 10%	(63.5 ± 10%)

Table 2. Impregnated Glass Fabric Properties

Property	LG-1000	LG1062	Test Method
Pressed Thickness, cured, mils/ply (µm/ply)	5.0 ± 1 (125)	2.0 (50)	Micrometer
Resin Content, %	65 ± 10	TBD	MIL-G-55636 4.6.6
Glass Fabric Style	108	106	MIL-G-55636 4.6.6
Flow, max., mils (µm)	5 (125)	5 (125)	IPC-2.3.17.1
Solder Resistance		No blistering or delamination after dip at 260°C (500°F) for 10 seconds or float at 260°C (500°F) for 30 seconds	IPC-2.4.13 Method A Method B
Peel, lbs/in (kN/m)	9 (1.6)	9 (1.6)	IPC-2.4.9 Method A
Dielectric Constant, (at 1 MHz)	3.5	TBD	IPC-2.5.5.3
Dissipation Factor, (at 1 MHz)	0.018	TBD	IPC-2.5.5.3
Dielectric Strength, V/mil (kV/mm)	2000 (80)	TBD	ASTM-D-149
Volatile Content, %	0.75	TBD	IPC-2.3.37

DuPont Electronic Materials
14 T.W. Alexander Drive
Research Triangle Park, NC 27709-4425
(800) 243-2143, Ext. 3637

www.dupont.com/fcm

The information set forth herein is furnished free of charge and based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill, at their own risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be taken as license to operate under or a recommendation to infringe any patents.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102.

Copyright © 2014 DuPont. All rights reserved. The DuPont Oval Logo, DuPont®, Mylar® and Pyralux® are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. K-28543 08/14