

IPC-4101 /98 /99 /101 /126 UL - File E41625 Grade PCL-FR-370HR

370HR is the industry's “best in class” lead-free compatible product for high-reliability applications across a wide range of markets.

PRODUCT FEATURES

Industry Recognition

- UL File Number: E41625
- Polyclad® Grade PCL-FR-370HR
- Qualified to UL's MCIL Program
- RoHS Compliant

Performance Attributes

- CAF resistant

Processing Advantages

- FR-4 process compatible
- UV blocking and AOI fluorescence
- Multiple reflow capable
- HDI technology compatible

PRODUCT AVAILABILITY

Standard Material Offering: Laminate

- 2 to 125 mil (0.05 to 3.2 mm)

Copper Foil Type

- HTE Grade 3
- RTF (Reverse Treat Foil)
- Embedded resistor foil

Copper Weight

- ½, 1 and 2 oz (18, 35 and 70 µm) available
- Heavier copper foil available
- Thinner copper foil available

Standard Material Offering: Prepreg

- Tooling of prepreg panels

Glass Fabric Availability

- E-glass
- Square weave glass
- Mechanically spread glass

370HR laminates and prepregs, designed by Polyclad, are made using a patented high performance 180°C Tg FR-4 multifunctional epoxy resin system that is designed for multilayer Printed Wiring Board (PWB) applications where maximum thermal performance and reliability are required. We manufacture 370HR laminates and prepregs with high quality E-glass glass fabric for superior Conductive Anodic Filament (CAF) resistance. 370HR provides superior thermal performance with low Coefficient of Thermal Expansion (CTE) and the mechanical, chemical and moisture resistance properties that equal or exceed the performance of traditional FR-4 materials.

370HR is used in thousands of PWB designs and has proven to be best in class for thermal reliability, CAF performance, ease of processing and proven performance on sequential lamination designs.

PRODUCT ATTRIBUTES



TYPICAL MARKET APPLICATIONS



ORDERING INFORMATION:

Contact your local sales representative or contact info@isola-group.com for further information.

Isola Group

6565 West Frye Road Chandler,
AZ 85226 Phone: 480-893-6527
Fax: 480-893-1409

Isola Asia Pacific

(Hong Kong) Ltd.12/F,
Kin Sang Commercial Centre,
49 King Yip Street, Kwun Tong,
Kowloon,
Hong Kong Phone: 852-2418-1318
Fax: 852-2418-1533

Isola GmbH

Isola Strasse 2 D-52348 Düren,
Germany Phone: 49-2421-8080
Fax: 49-2421-808164

Typical Values Table

Property		Typical Value	Units	Test Method
			Metric (English)	IPC-TM-650 (or as noted)
Glass Transition Temperature (Tg) by DSC		180	°C	2.4.25C
Decomposition Temperature (Td) by TGA @ 5% weight loss		340	°C	2.4.24.6
Time to Delaminate by TMA (Copper removed)	A. T260	60	Minutes	2.4.24.1
	B. T288	30		
Z-Axis CTE	A. Pre-Tg	45	ppm/°C	2.4.24C
	B. Post-Tg	230	ppm/°C	
	C. 50 to 260°C, (Total Expansion)	2.8	%	
X/Y-Axis CTE	Pre-Tg	13/14	ppm/°C	2.4.24C
Thermal Conductivity		0.4	W/m·K	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 100 MHz	4.24	—	2.5.5.3
	B. @ 1 GHz	4.17		2.5.5.9
	C. @ 2 GHz	4.04		Bereskin Stripline
	D. @ 5 GHz	3.92		Bereskin Stripline
	E. @ 10 GHz	3.92		Bereskin Stripline
Df, Loss Tangent	A. @ 100 MHz	0.0150	—	2.5.5.3
	B. @ 1 GHz	0.0161		2.5.5.9
	C. @ 2 GHz	0.0210		Bereskin Stripline
	D. @ 5 GHz	0.0250		2.5.5.5
	E. @ 10 GHz	0.0250		2.5.5.5
Volume Resistivity	A. After moisture resistance B. At elevated temperature	3.0 x 10 ⁸ 7.0 x 10 ⁸	MΩ-cm	2.5.17.1
Surface Resistivity	A. After moisture resistance B. At elevated temperature	3.0 x 10 ⁶ 2.0 x 10 ⁸	MΩ	2.5.17.1
Dielectric Breakdown		>50	kV	2.5.6B
Arc Resistance		115	Seconds	2.5.1B
Electric Strength (Laminate & laminated prepreg)		54 (1350)	kV/mm (V/mil)	2.5.6.2A
Comparative Tracking Index (CTI)		3 (175-249)	Class (Volts)	UL 746A ASTM D3638
Peel Strength	A. Low profile copper foil and very low profile copper foil all copper foil >17 µm [0.669 mil]	1.14 (6.5)	N/mm (lb/inch)	2.4.8C
	B. Standard profile copper	1.25 (7.0)		2.4.8.2A
	1. After thermal stress	1.25 (7.0)		2.4.8.3
	2. At 125°C (257°F)	1.14 (6.5)		2.4.8.3
Flexural Strength	A. Length direction	620 (90.0)	MPa (kpsi)	2.4.4B
	B. Cross direction	531 (77.0)		
Tensile Strength	A. Length direction	385 (55.9)	MPa (kpsi)	ASTM D3039
	B. Cross direction	245 (35.6)		
Young's Modulus	A. Length direction	3744	ksi	ASTM D790-15e2
	B. Cross direction	3178		
Poisson's Ratio	A. Length direction B. Cross direction	0.177 0.171	—	ASTM D3039
Moisture Absorption		0.15	%	2.6.2.1A
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94
Relative Thermal Index (RTI)		130	°C	UL 796

NOTES

Visit our site <http://www.isola-group.com> for more details.

Revisions:

A: Initial release - 4/17

B: Corrected units for Flexural and Tensile Strength - 8/18

C: Change MOT to RTI 5/19

D: Changed VLP2 to HVLP to align with common industry terms 4/21

E: Corrected Lengthwise Flexural strength value typo from 6201 to 620 - 6/24

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2021 Isola Group. All rights reserved.