

IPC-4101 /24 /121 /124 UL - File Number E41625

FR408 is a high-performance FR-4 epoxy laminate and prepreg system designed for advanced circuitry applications.

PRODUCT FEATURES

Industry Recognition

- UL File Number: E41625
- Qualified to UL's MCIL Program
- RoHS Compliant

Performance Attributes

Processing Advantages

- FR-4 process compatible
- UV blocking and AOI fluorescence

PRODUCT AVAILABILITY

Standard Material Offering: Laminate

- 2 to 125 mil (0.05 to 3.2 mm)
- Available in full size sheet or panel form

Copper Foil Type

- HTE Grade 3
- RTF (Reverse Treat Foil)

Copper Weight

- ½ to 2 oz (18 to 70 µm) available
- Heavier copper available
- Thinner copper foil available

Standard Material Offering: Prepreg

- Roll or panel form
- Tooling of prepreg panels

Glass Fabric Availability

- E-glass
- Square weave glass

Its low dielectric constant (Dk) and low dissipation factor (Df) make it an ideal candidate for broadband circuit designs requiring faster signal speeds or improved signal integrity. FR408 is compatible with most FR-4 processes. This feature allows the use of FR408 without adding complexity to current fabrication techniques.

PRODUCT ATTRIBUTES



TYPICAL MARKET APPLICATIONS



ORDERING INFORMATION:

Contact your local sales representative or contact info@isola-group.com for further information.

Isola Group

6565 West Frye Road Chandler,
 AZ 85226 Phone: 480-893-6527
 Fax: 480-893-1409

Isola Asia Pacific

(Hong Kong) Ltd. 12/F,
 Kin Sang Commercial Centre,
 49 King Yip Street, Kwun Tong,
 Kowloon,
 Hong Kong Phone: 852-2418-1318
 Fax: 852-2418-1533

Isola GmbH

Isola Strasse 2 D-52348 Düren,
 Germany Phone: 49-2421-8080
 Fax: 49-2421-808164

Typical Values Table

Property		Typical Value	Units	Test Method
			Metric (English)	IPC-TM-650 (or as noted)
Glass Transition Temperature (Tg) by DSC		180	°C	2.4.25C
Decomposition Temperature (Td) by TGA @ 5% weight loss		360	°C	2.4.24.6
Time to Delaminate by TMA (Copper removed)	A. T260 B. T288	60 15	Minutes	2.4.24.1
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	60 228 3.5	ppm/°C ppm/°C %	2.4.24C
X/Y-Axis CTE	Pre-Tg	13	ppm/°C	2.4.24C
Thermal Conductivity		0.4	W/m-K	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 100 MHz B. @ 1 GHz C. @ 2 GHz D. @ 5 GHz E. @ 10 GHz	3.69 3.66 3.67 3.66 3.65	—	2.5.5.3 2.5.5.9 Bereskin Stripline Bereskin Stripline Bereskin Stripline
Df, Loss Tangent	A. @ 100 MHz B. @ 1 GHz C. @ 2 GHz D. @ 5 GHz E. @ 10 GHz	0.0094 0.0117 0.0120 0.0127 0.0125	—	2.5.5.3 2.5.5.9 Bereskin Stripline Bereskin Stripline Bereskin Stripline
Volume Resistivity	A. After moisture resistance B. At elevated temperature	4.6×10^7 2.8×10^8	MΩ-cm	2.5.17.1
Surface Resistivity	A. After moisture resistance B. At elevated temperature	2.81×10^6 2.64×10^8	MΩ	2.5.17.1
Dielectric Breakdown		>50	kV	2.5.6B
Arc Resistance		120	Seconds	2.5.1B
Electric Strength (Laminate & laminated prepreg)		55 (1400)	kV/mm (V/mil)	2.5.6.2A
Comparative Tracking Index (CTI)		3 (175-249)	Class (Volts)	UL 746A ASTM D3638
Peel Strength	A. Low profile copper foil and very low profile copper foil all copper foil >17 μm [0.669 mil] B. Standard profile copper 1. After thermal stress 2. At 125°C (257°F) 3. After process solutions	1.14 (6.5) 1.225 (7.0) 1.14 (6.5) 0.90 (5.1)	N/mm (lb/inch)	2.4.8C 2.4.8.2A 2.4.8.3 2.4.8.3
Flexural Strength	A. Length direction B. Cross direction	81.4 64.1	ksi	2.4.4B
Tensile Strength	A. Length direction B. Cross direction	59.3 42.0	ksi	ASTM D3039
Young's Modulus	A. Length direction B. Cross direction	3685 3044	ksi	ASTM D790-15e2
Poisson's Ratio	A. Length direction B. Cross direction	0.162 0.138	—	ASTM D3039
Moisture Absorption		0.15	%	2.6.2.1A
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94
Relative Thermal Index (RTI)		130	°C	UL 796

NOTES

Visit our site <http://www.isola-group.com> for more details.

Revisions:

A: Initial release - 4/17

B: Corrected units for Flexural and Tensile Strength - 8/18

C: Change MOT to RTI 5/19

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2021 Isola Group. All rights reserved.