

TerraGreen®

Halogen-free, Very Low Loss Material Tg 200°C Td 390°C Dk 3.44 Df 0.0039

IPC-4103 /17 IPC-4101 /102 UL - File Number E41625

TerraGreen® laminate materials exhibit exceptional electrical properties which are very stable over a broad frequency and temperature range.

PRODUCT FEATURES

Industry Recognition

RoHS Compliant

Performance Attributes

Lead-free assembly compatible

Processing Advantages

- FR-4 process compatible
- UV blocking and AOI fluorescence

PRODUCT AVAILABILITY

Standard Material Offering: Laminate

- Available in full size sheet or panel form Copper Foil Type
 - HTE Grade 3

Copper Weight

- ½ to 2 oz (18 to 70 μm) available
- Thinner copper foil available

Standard Material Offering: Prepreg

- · Roll or panel form
- Tooling of prepreg panels

Glass Fabric Availability

- E-glass
- Square weave glass
- Mechanically spread glass

TerraGreen[®] is engineered for such highperformance applications as power amplifier boards for LTE base stations, internet infrastructure and cloud computing. TerraGreen [®] features a Dielectric Constant (Dk) that is stable between -55°C and 125°C, up to 20 GHz.

TerraGreen[®] is a lead-free assembly material and is easy to process. This high-performance material utilizes a short-lamination cycle; the product is easy to drill, does not require plasma desmear, and the prepreg shelf life is similar to FR-4 materials. TerraGreen[®] is suitable for high-layer count, high-speed digital backplanes and is compatible with Isola's FR-4 materials for hybrid designs.

TerraGreen[®] meets UL 94 V-0 and is halogen free.

PRODUCT ATTRIBUTES







TYPICAL MARKET APPLICATIONS





ORDERING INFORMATION:

Contact your local sales representative or contact info@isola-group.com for further information.

Isola Group

6565 West Frye RoadChandler, AZ 85226 Phone: 480-893-6527 Fax: 480-893-1409

Isola Asia Pacific

(Hong Kong) Ltd.12/F, Kin Sang Commercial Centre, 49 King Yip Street, Kwun Tong, Kowloon,

Hong KongPhone: 852-2418-1318 Fax: 852-2418-1533

Isola GmbH

Isola Strasse 2 D-52348 Düren, GermanyPhone: 49-2421-8080 Fax: 49-2421-808164

Typical Values Table

Property			Units	Test Method
		Typical Value	Metric (English)	IPC-TM-650 (or as noted)
Glass Transition Temperature (Tg) by DSC		200	°C	2.4.25C
Decomposition Temperature (Td) by TGA @ 5% weight loss		390	°C	2.4.24.6
Time to Delaminate by TMA (Copper removed)	A. T260 B. T288	60	Minutes	2.4.24.1
Z-Axis CTE	50 to 260°C, (Total Expansion)	2.9	%	2.4.24C
X/Y-Axis CTE	Pre-Tg	16	ppm/°C	2.4.24C
Thermal Conductivity		0.32	W/m·K	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 2 GHz B. @ 5 GHz C. @ 10 GHz	3.44	_	2.5.5.5
Df, Loss Tangent	A. @ 2 GHz B. @ 5 GHz C. @ 10 GHz	0.0039	_	Bereskin Stripline
Volume Resistivity	C-96/35/90	1.33 x 10 ⁷	MØ-cm	2.5.17.1
Surface Resistivity	C-96/35/90	1.33 x 10 ⁵	MI	2.5.17.1
Dielectric Breakdown		45.4	kV	2.5.6B
Arc Resistance		139	Seconds	2.5.1B
Electric Strength (Laminate & laminated prepreg)		45 (1133)	kV/mm (V/mil)	2.5.6.2A
Comparative Tracking Index (CTI)		2	Class (Volts)	UL 746A ASTM D3638
Peel Strength	A. 0.5 oz. EDC foil B. 1 oz. EDC foil	0.88 (5.0)	N/mm (lb/inch)	2.4.8C
Flexural Strength	A. Length direction B. Cross direction	75.5 60.0	ksi	2.4.4B
Tensile Strength	A. Length direction B. Cross direction	40.0 39.0	ksi	ASTM D3039
Young's Modulus	A. Length direction B. Cross direction	3125 2745	ksi	ASTM D790-15e2
Poisson's Ratio	A. Length direction B. Cross direction	0.238 0.231	_	ASTM D3039
Moisture Absorption		0.05	%	2.6.2.1A
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94
Relative Thermal Index (RTI)		130	°C	UL 796

NOTES

Visit our site http://www.isola-group.com for more details.

Revisions:

- A: Initial release 4/17
- B: Corrected units for Flexural and Tensile Strength 8/18
- C: Change MOT to RTI 5/19
- D: Added CTI value 01/20
- E: Changed VLP2 to HVLP to align with common industry terms 4/21

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries. Copyright © 2021 Isola Group. All rights reserved.